



A KNP BT company

ANALYSIS REPORT

Requisition #: 96485

December 12, 1996

Requisitioner: Mark Mayronne

Samples to be Tested: Foil Laminates labeled: FBBF; FBF; FCBR; PET FOIL one side

Testing Requested: Puncture Resistance

Test Method Used: ASTM F1306

Puncture Resistance Results (lbs.)

FBBF - 12.31 lbs.

FBF - 9.29 lbs.

FCBR - 6.03 lbs.

PET FOIL - 16.97 lbs.

If you have any questions, please contact me at (518) 743-3294. Thanks.

Testing Completed By: *Mary Ringer*
Mary Ringer
AVI Technical Services
Glens Falls, NY 12801